



## Technical Data Sheet

# Cocoa Paper Dark

## 45% cocoa shell material

### TYPICAL VALUES

COCOA PAPER DARK						
	Units	115	170	250	350	
<b>Substance</b>	g/m <sup>2</sup>	115	170	250	350	ISO 536
<b>Thickness</b>	µm	240	320	400	540	ISO 534
<b>Moisture</b>	%	6,8	6,8	6,8	6,8	ISO 287
<b>Cobb60</b>	g/m <sup>2</sup>	30	30	30	30	ISO 535
<b>Bendtsen Roughness</b>	ml/mn	1800	1800	1800	1800	ISO 8791

Testing environment conditions as per ISO 187: 50% RH / T = 23°C  
Paperboard is recyclable

**TAPPI** - Technical Association of the Pulp and Paper Industry  
**ISO** - International Standard Organization

**Oil & Grease Resistance**- Treatment available on demand

**Food contact.** Compliant with the Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch. I §§ 176.170 and 176.180. Compliant with BFRXXXVI





## Technical Data Sheet

# Cocoa Paper Milk

## 25% cocoa shell material

### TYPICAL VALUES

COCOA PAPER MILK						
	Units	115	170	250	350	
<b>Substance</b>	g/m <sup>2</sup>	115	170	250	350	ISO 536
<b>Thickness</b>	µm	220	290	380	540	ISO 534
<b>Moisture</b>	%	6,8	6,8	6,8	6,8	ISO 287
<b>Cobb60</b>	g/m <sup>2</sup>	30	30	30	30	ISO 535
<b>Bendtsen Roughness</b>	ml/mn	1800	1800	1800	1 800	ISO 8791

Testing environment conditions as per ISO 187: 50% RH / T = 23°C  
Paperboard is recyclable

**TAPPI** - Technical Association of the Pulp and Paper Industry  
**ISO** - International Standard Organization

**Oil & Grease Resistance**- Treatment available on demand

**Food contact.** Compliant with the Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch. 1 §§ 176.170 and 176.180. Compliant with BFRXXXVI

