







Carbon Neutral Cocoa Fibers









Technical Data Sheet

Cocoa Paper Milk 25% cocoa shell material

TYPICAL VALUES*

COCOA PAPER MILK					
	Units	80	110	150	
Substance	g/m²	80	110	150	ISO 536
Thickness	μm	110	145	190	ISO 534
Moisture	%	6,5	6,5	6,5	ISO 287
Bekk smoothness	sec	17	15	13	ISO 8791
Bursting resistance	KPa	310	400	460	ISO 2758

*Indicative values (product still under development)

Testing environment conditions as per ISO 187: 50% RH / T = 23°C Paperboard is recyclable

TAPPI - Technical Association of the Pulp and Paper Industry ISO - International Standard Organization

Oil & Grease Resistance - Treatment on demand

Food contact. Compliant with the Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch. I §§ 176.170 and 176.180. Compliant with BFRXXXVI and BFRXXXVI-2,

Made in France



```
16/05/2019
```